

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
10 May 2001 (10.05.2001)

PCT

(10) International Publication Number
WO 01/32226 A1

- (51) International Patent Classification⁷: A61L 15/20, 15/46, 15/60
- (21) International Application Number: PCT/NL00/00797
- (22) International Filing Date:
3 November 2000 (03.11.2000)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
99203622.8 3 November 1999 (03.11.1999) EP
- (71) Applicant (for all designated States except US): SCA
HYGIENE PRODUCTS ZEIST B.V. [NL/NL]; P.O. Box
360, NL-3700 AJ Zeist (NL).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): BESEMER, Arie
[NL/NL]; H.v.d. Boschstraat 111, NL-3958 CC Ameron-
gen (NL). VERWILLIGEN, Anne-Mieke [NL/NL];
Oude Arnhemseweg 234, NL-3705 BJ Zeist (NL).
THORNTON, Jeffrey [US/NL]; Jagersweg 13, NL-1272
AL Huizen (NL).
- (74) Agent: JORRITSMA, Ruurd; Nederlandsch Octrooibu-
reau, Scheveningseweg 82, P.O. Box 29720, NL-2502 LS
The Hague (NL).
- (81) Designated States (national): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ,
DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR,
HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR,
LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ,
NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM,
TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.
- (84) Designated States (regional): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian
patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European
patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE,
IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF,
CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).
- Published:**
- With international search report.
 - Before the expiration of the time limit for amending the
claims and to be republished in the event of receipt of
amendments.
- For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: ALKALI-NEUTRALISING SUPERABSORBENT PRODUCTS

(57) Abstract: A superabsorbent article of the invention having improved odour control and microbial control, comprises a liquid-impervious back layer, a liquid-absorbing intermediate layer containing a partially neutralised, acidic hydrophilic polymer, especially a surface-crosslinked polyacrylate, and a liquid-pervious, non-absorbing top layer, and is characterised by comprising an alkali-neutralising agent which is evenly distributed in said absorbing intermediate layer.

WO 01/32226 A1

Alkali-neutralising superabsorbent products

[0001] The present invention relates to a superabsorbent article, which has enhanced odour control and prevents bacterial growth, and to a method of producing such an article.

5 [0002] Superabsorbent materials for use in baby diapers, feminine hygiene products and incontinence pads of various types are known in the art. They usually contain a strongly hydrophilic crosslinked polymer of the partially neutralised polyacrylate type. A problem of such hydrophilic particles, however, is that the granular polymers have a tendency to clump, "gel block", which reduces inter-particle porosity and limits the swelling rate.

10 Therefore, many superabsorbent materials are nowadays of an advanced type, i.e. with additional surface-crosslinking resulting in improved dispersibility and increased absorption rate. The surface crosslinking can be effected with e.g. diglycidyl compounds or alkylene carbonates at high temperature. It results in membrane-like surface properties and hence in enhanced water transport (swelling behaviour) and in better mechanical

15 properties (higher absorption under load) (for a review, see e.g. Buchholz and Graham, *Modern Superabsorbent Polymer Technology*, Wiley - VCH, 1998, especially Ch. 3: *Commercial processes for the manufacture of superabsorbent polymers* and Ch. 5: *The structure and properties of superabsorbent polyacrylates*, and references cited therein).

[0003] A problem related to the use of superabsorbent materials is the odour caused by

20 urine components, especially ammonia and other alkaline nitrogen-containing compounds. These components cause superabsorbent materials to become objectionable long before their maximum absorbing capacity has been used. Also bacterial growth may lead to products that are odorous and/or irritating to the skin. Consequently, there is a need for superabsorbent materials, which have odour control and reduced bacterial growth

25 when contacted with body fluids, while retaining the effective absorption and dispersibility of the "modern" superabsorbent polymers.

[0004] It has been proposed to incorporate pH controlling agents or ammonia absorbing agents into diapers to reduce the odour and bacterial growth problems and skin irritation ("diaper rash"). EP-A-202,127 discloses absorbent articles of the first generation type (not

30 surface-crosslinked) on the basis of particulate, highly (>50%, especially >65%) neutralised polyacrylate, in which about 10 % by weight of polymeric pH control agents such as non-neutralised polyacrylic acid, cellulose phosphate are non-uniformly distributed in discrete zones of the absorbent article. Non-polymeric pH controlling agents

such as citric acid are also claimed, but are not illustrated in EP-202,127. The non-uniform distribution means that some zones should have a high acid/absorbent ratio of at least 10/1, while other zones should have a low acid/absorbent ratio of no more than 1/10. It is stated that the non-uniform distribution is necessary as simple combination of the pH control agents with the superabsorbent polymer in the same structure cannot be accomplished without difficulty, i.e. only with considerable lowering of the absorption capacity.

[0005] EP-A-311,344 discloses incontinence absorbent articles for reducing diaper rash, which contain an antimicrobial agent and a pH buffering agent which together keep the pH of absorbed bicarbonate-containing, *Proteus vulgaris*-contaminated urine at below 7.5. The buffering agent is partly neutralised acrylate or another acid.

[0006] It was surprisingly found now that an effective odour control can be achieved by evenly distributing a low molecular weight alkali-neutralising (pH controlling) compound in the absorbent article, while retaining the high absorptive power of non-acidic absorbent polymers, including the surface-crosslinked types. Thus the invention pertains to a super-absorbent article having improved odour control and microbial control, comprising a liquid-impervious back layer, a liquid-absorbing intermediate layer containing a partially neutralised acidic hydrophilic polymer, and a liquid-pervious, non-absorbing top layer, and further comprising an alkali-neutralising agent, wherein the alkali-neutralising agent is distinguished from the partially neutralised acidic hydrophilic polymer and is evenly distributed in said absorbing intermediate layer.

[0007] The superabsorbent polymer may be any type of hydrophilic polymer, typically on the basis of synthetic polymers of unsaturated carboxylic acids, such as polyacrylate and/or polymaleate. The superabsorbent polymer is preferably surface-crosslinked, i.e. of the type having particles with distinct relatively rigid outer layer layers and relatively weak, high-swelling internal gel bodies. The superabsorbent polymer is preferably not acidic itself, i.e. is highly neutralised in case of acidic polymers and – without the alkali-neutralising agent - has a pH above 5, especially above 5.5, more especially above 5.8, upon wetting, in order to have sufficient absorptive capacity. Therefore, the acidic polymer has a degree of neutralisation of at least 50%, especially between 60 and 80%.

[0008] Suitable alkali-neutralising (acidifying) agents include organic di- or polycarboxylic acid acids such as maleic, fumaric, oxalic, malonic, succinic, and similar acids, and especially hydroxyacids such as citric, gluconic, ascorbic, glycolic, glyceric, lactic,

malic, tartaric, salicylic acid and the like, as well as benzoic acid and phosphoric and other inorganic acids. These acids may be used in combination with their partially neutralised salts (e.g. monosodium citrate or monopotassium phosphate) to provide buffering capacity. Also, neutral materials ("hidden acids"), especially internal esters and anhydrides of the acids can be incorporated for lowering the pH. These include acid
5 lactides (lactide, glycolide), anhydrides, e.g. maleic anhydride, succinic anhydride, and γ - and δ -lactones, such as gluconolactone. These lactides, anhydrides and lactones can act in two ways: they can hydrolyse to produce a neutralising acid, or they can react with an amine to produce an amide; either way results in eliminating the amines and other
10 undesired components. The type and the amount of the alkali-neutralising agents should be such that the pH of the absorbent layer, when wetted is 5.6 or lower, down to e.g. pH 3.5, preferably between 5.0 and 4.0.

[0009] The alkali-neutralising agents can also be present in slow-release form such as capsules, granules or small tablets with a slowly dissolving layer of e.g. linear dextrans or
15 other slowly dissolving material. Such capsules, granules or small tablets may have dimensions of e.g. 50 - 250 μm and are evenly distributed through the absorbing material.

[0010] The absorption capacity can be expressed as free swelling capacity (FSC) and the centrifugal retention capacity (CRC), and with the absorption under load (AUL), or with other suitable parameters, using a modified synthetic urine (SU) as test liquid. The
20 composition of this synthetic urine, which simulates urine also in that it is buffered, is as follows: 300 mM urea, 60 mM KCl, 130 mM NaCl, 2.0 mM CaSO_4 , 3.5 mM MgSO_4 , 29 mM KH_2PO_4 , 5.3 mM Na_2HPO_4 , 1 mg/l Triton X-100 in deionised water.

[0011] The superabsorbent articles of the invention can be used for absorbing liquids, especially of body fluids containing various salts and non-ionic substances, together with
25 alkaline and/or malodorous components. The articles are particularly suitable in the form of absorbent hygiene articles, such as diapers, sanitary towels, incontinence pads and the like. Such articles can be produced entirely on the basis of the single superabsorbent polymers such as polyacrylates and polymaleates, but they can also contain a mixture of absorbent materials, such as different polyacrylates, cellulose derivatives and other
30 polysaccharides.

[0012] The absorbent article is preferably a layered product, in which the superabsorbent polymer constitutes at least one layer. The absorbent layer can be located between a liquid-pervious top layer and a liquid-impervious bottom layer. In particular the product

may have four layers. The first one can be a thin, non-woven layer of polyester fibres or other fibres. The second layer can be a wadding which is used for acquiring and spreading the absorbed fluid such as urine. The third layer can consist of fluff pulp wherein the superabsorbent polymer is spread as fine particles, especially 50-800 μm . The last layer
5 can be a back sheet of a water-resistant material such as polyethylene, which prevents leakage from the layered absorption product. The product may instead have three layers, in which the fluff layer and the absorbent layer are combined. In either form, the neutralising compound is evenly distributed with the superabsorbent polymer through the fluff.

10

Example 1:

Sanitary towels having an upper core and a lower core and a size of 10 * 28 cm were produced. The upper core contained MS CTMP pulp (350 g/m^2) and 15 wt.% of super-absorbent polymer (SAP), the lower core contained KEA pulp (310 g/m^2) and 21 wt.% of
15 SAP. Thus, the total weight of the cores is $(0.10 * 0.28 * 350 * 1.15) + (0.10 * 0.28 * 310 * 1.21) \text{ g} = 21.8 \text{ g}$. The bulk volume was $8 \text{ cm}^3/\text{g}$. The SAP was either highly neutralised polyacrylate (IM7100) or acidic (30% neutralised) polyacrylate (IM7110). IM7100 has a better absorptive power than IM7110. To the SAP, an acid was added in the amounts given below. Gluconic acid was added as a 50% (w/w) solution, citric acid was added as a
20 powder or a crushed tablet. The towel was contacted with modified synthetic urine (SU, see above). The absorption capacity (AC) was measured in g of liquid absorbed by the towel per g of product (superabsorbent polymer plus pulp). The towel is placed on a 30° inclined Perspex test plate, the lower 2-3 cm being immersed in the test liquid (SU). The acquisition time (AT) was measured as the time needed to take up 50 ml of the test liquid
25 per towel and was measured three times consecutively. The results are given below.

SAP	Acid	Amount (mmoles)	pH (wet)	AC (g/g)	AT (sec)
IM7100	-	-	5.9	11.4	14, 14, 20
IM7110	-	-	5.0	10.5	19, 21, 32
IM7100	Gluconic	1.9	5.6	11.3	
IM7100	Gluconic	3.9	5.2	11.1	
IM7100	Gluconic	5.6	5.0	10.8	
IM7100	Gluconic	6.9	4.8	10.4	
IM7100	Gluconic	9.1	4.3	10.5	
IM7100	Citric *	6.2	4.7	11.5	14, 15, 21
IM 7100	Citric *	8.3	4.3	11.4	14, 16, 21
IM 7100	Citric *	10.4	4.0	10.9	15, 17, 24

* added as powder

Claims

1. A superabsorbent article having improved odour control and microbial control, comprising a liquid-impervious back layer, a liquid-absorbing intermediate layer containing a surface-crosslinked, partially neutralised, acidic hydrophilic polymer, and a liquid-pervious, non-absorbing top layer, characterised by comprising an alkali-neutralising agent which is evenly distributed in said absorbing intermediate layer.
2. A superabsorbent article according to claim 1, in which the alkali neutralising agent is an organic acid selected from maleic, fumaric, oxalic, malonic, succinic, citric, gluconic, ascorbic, glycolic, glyceric, lactic, malic, tartaric and salicylic acid, especially citric, malic or lactic acid.
3. A superabsorbent article according to claim 1, in which the alkali neutralising agent is selected from anhydrides, lactides and lactones, especially dilactide, glycolide, butyrolactone, valerolactone, gluconolactone and maleic anhydride.
4. A superabsorbent article according to any one of claims 1-3, in which the alkali neutralising agent is present in amount of 0.2 to 1 weight part per weight part of hydrophilic polymer.
5. A superabsorbent article according to any one of claims 1-4, in which the article contains a cellulosic carrier material in an amount of 2 to 10 weight parts per weight part of hydrophilic polymer.
6. A superabsorbent article according to any one of the preceding claims, in which the hydrophilic polymer comprises polyacrylate.
7. A superabsorbent article according to any one of the preceding claims, in which the acidic polymer has a degree of neutralisation of at least 50%, especially between 60 and 80%.

8. A superabsorbent article according to any one of the preceding claims, in which the absorbing layer, after humidification with neutral water, has a pH of 5.6 or lower.
9. A superabsorbent article according to claim 9, in which the absorbing layer, after humidification with neutral water, has a pH between 3.5 and 5.0.
10. A superabsorbent article according to any one of the preceding claims, which contains 2.5 to 10 g of hydrophilic polymer.
11. A process for producing a superabsorbent article having improved odour control and microbial control, comprising mixing an alkali-neutralising agent with a surface-crosslinked, highly neutralised acidic hydrophilic polymer, distributing the mixture in a fibrous carrier material, working the carrier material into a layer and covering the layer of carrier material with a liquid-impervious layer on one side and with a liquid-pervious, non-absorbing layer, at the other side.

INTERNATIONAL SEARCH REPORT

Int. l. Application No

PCT/NL 00/00797

A. CLASSIFICATION OF SUBJECT MATTER
 IPC 7 A61L15/20 A61L15/46 A61L15/60

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
 IPC 7 A61L A61F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, PAJ, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 761 241 A (NIPPON CATALYTIC CHEM IND) 12 March 1997 (1997-03-12) page 8, line 39 - line 57 claims	1,2,4-11
X	WO 95 19191 A (WEYERHAEUSER CO) 20 July 1995 (1995-07-20) page 11, line 21 -page 12, line 2 page 39, line 15 -page 41, line 26 claims 1,18,19,29,30,39,48,51,58,59,78,80,81,83 -/-	1,2,4-11

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *Z* document member of the same patent family

Date of the actual completion of the international search

6 March 2001

Date of mailing of the international search report

13/03/2001

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
 NL - 2280 HV Rijswijk
 Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
 Fax: (+31-70) 340-3016

Authorized officer

Thornton, S

INTERNATIONAL SEARCH REPORT

International Application No

PCT/NL 00/00797

G.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 95 22655 A (WEYERHAEUSER CO) 24 August 1995 (1995-08-24) page 22, line 25 -page 23, line 20 page 30, line 22,43 page 38, line 16 - line 27 page 40, line 24 -page 41, line 17 example 12 claims	1-11
A	EP 0 311 344 A (PROCTER & GAMBLE) 12 April 1989 (1989-04-12) page 5, line 16 - line 57 page 6, line 14 - line 28 claims	1-7,9,10
A	US 3 707 148 A (BRYCE DOUGLAS MAXWELL) 26 December 1972 (1972-12-26) column 4, line 37 - line 66 examples 1,2 claims 1-8	1,2,4,5, 9,10

INTERNATIONAL SEARCH REPORT

Int. l. Application No

PCT/NL 00/00797

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0761241 A	12-03-1997	JP 9157534 A	17-06-1997
		JP 9124955 A	13-05-1997
		JP 2000342963 A	12-12-2000
		KR 197888 B	15-06-1999
		US 5797893 A	25-08-1998
WO 9519191 A	20-07-1995	AU 1527195 A	01-08-1995
		EP 0739217 A	30-10-1996
		US 5998032 A	07-12-1999
WO 9522655 A	24-08-1995	US 5547541 A	20-08-1996
		AU 1921395 A	04-09-1995
		CA 2181476 A	24-08-1995
		EP 0745160 A	04-12-1996
		JP 9509226 T	16-09-1997
		US 5807364 A	15-09-1998
EP 0311344 A	12-04-1989	US 4842593 A	27-06-1989
		AT 116554 T	15-01-1995
		AU 2358188 A	13-04-1989
		CA 1306080 A	11-08-1992
		DE 3852686 D	16-02-1995
		DE 3852686 T	13-07-1995
		ES 2065916 T	01-03-1995
		FI 884643 A, B,	10-04-1989
		HK 99796 A	14-06-1996
		IE 65775 B	15-11-1995
		JP 2001265 A	05-01-1990
		JP 2760814 B	04-06-1998
		KR 131462 B	14-04-1998
		MX 172295 B	13-12-1993
US 3707148 A	26-12-1972	BE 751464 A	04-12-1970
		CH 515692 A	30-11-1971
		DE 2027809 A	10-12-1970
		FR 2049996 A	26-03-1971
		GB 1317156 A	16-05-1973
		NL 7008200 A	08-12-1970
		ZA 7003733 A	27-01-1971

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☒ **FADED TEXT OR DRAWING**
- ☒ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER: _____**

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.